

### EASY FLOW

1 component water-based PU acrylate for parquet and wooden surfaces. Gives a clear protection to the wood.

Easy to use, universal and neutral in overlaps

- » Good processing properties.
- » Easy to apply
- » Good chemical and mechanical resistance.

#### TECHNICAL DATA

<b>Product type</b>	waterborne
<b>Cleaning</b>	water
<b>Gloss level</b>	Matt 15 Satin 40
<b>Viscosity</b>	+/-25 sec - DIN 4mm
<b>Solids content</b>	+/- 31%
<b>Sold by case</b>	4 x 5 L
<b>Coverage</b>	10-12 m <sup>2</sup> /liter per coat 100-130 sq.ft./L per coat
<b>Drying times</b>	
Dust dry:	after 20 to 30 minutes
Sandable:	after 4 to 6 hours
Load-bearing:	after 24 hours
Fully hardened:	after +/- 7 days
<b>Sanding grit</b>	P 120-150
<b>Storage/transport</b>	between 5°C and 25°C
<b>Shelf life</b>	12 months in the original and unopened packaging.
<b>Disposal</b>	Dispose of residue and empty packaging in accordance with local ordinances.

Ciranova® products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However they are drawn to our best knowledge and ability, the user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.



5L



#### PREPARATION

Make sure all prior coatings are completely removed and the wood surface is free from dust and other contamination.

Can be used on sanded, planed and brushed wood. For under-floor heating, exotic wood and cork, FORTICO sealer is recommended as primer.

#### APPLICATION

Use EASY FLOW 1C as a primer and finishing coat. Apply the product by brush or roller in 3 coats.

First coat: apply approx. 80-100 g/m<sup>2</sup> and leave to dry for approx. 4 hours.

Second coat: apply approx. 80-100 g/m<sup>2</sup> in the same manner as the first coat and leave to dry for +/- 6 hours.

Afterwards intermediate sanding with 180-220 grain, remove dust and apply the third coat approx. 80-100 g/m<sup>2</sup>.

#### DRYING TIMES

Dust dry: after 20 to 30 minutes.

Recoatable : after 4 to 6 hours.

Drying times are dependent on the applied quantity, temperature, humidity and ventilation.

#### MAINTENANCE

Regular maintenance with Hard Floor Fresh Ciranova®. Use UNICARE X-MATT or Hard floor Polish for periodic maintenance. Hard Floor Cleaner Ciranova® is used for cleaning highly soiled floors and to remove old layers of polish.

#### IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately afterwards. For industrial applications, consult Ciranova® technical services. **Water-based products can develop skins after contact with air. Filter beforehand, if necessary.**