

# Reactive stain



5L

1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

**Produced by Debal Coatings nv**  
Industrieweg 29 - 8800 Beveren-Roeselare  
Belgium  
tel. +32 (0) 51 30 11 40  
fax +32 (0) 51 31 26 48  
ciranova@ciranova.be

## PRODUCT DESCRIPTION

Reactive waterbased ageing stain based on natural and reactive dyes. Reactive stains are specially fit for the ageing of wood containing tannin such as oak and pine. Reactive stains react with the tannin in the wood and give the wood a unique aged finish. Only for interior use.

## TECHNICAL DATA

COLOURS	available in 16 colours
LUSTRE	-
DENSITÉ	+/- 1,00 kg/l
VISCOSITY	like water

## PREPARATION

Can be used on sanded, planed and brushed wood.  
The wood can be slightly wettened first to avoid overlaps.

## USER TIPS

Stir and mix the stain before use. Apply the reactive stain with a brush in the direction of the wood fiber and equalize with a dry brush.  
ATTENTION: As it's a reactive stain, be sure you apply the reactive stain evenly.  
Reactive stain can also be applied with a pressure sprayer. Afterwards also equalize the stain.



## DRYING TIMES

At least 6 hours (reaction time) at room temperature.



## APPLYING QUANTITY

10-15m<sup>2</sup>/l, depending on the type of wood, preparation, sanding...

## AFTER TREATMENT

After drying, flatten the raised wood grain with a green buffing pad. Afterwards Ciranova oil or wax can be applied to finish the surface. To finish with varnish or lacquer, please contact our technical service.

## PRODUCT INFORMATION

Available in 16 colors.  
Storage life: 1 year in original and unopened packaging.  
Must be stored frost free.

## SPECIAL QUALITIES

Only use stainless material. After use, clean the material with water. This product should not be poured into drains.

**Wood preparation, the type of wood, quantity applied etc. may affect the final colour. For this reason always make a test first!**